



Technical centre

Luxus Limited, Belvoir Way, Fairfield Industrial Estate, Louth, Lincolnshire, LN11 0LQ

Tel: + 44 (0) 1507 604941 • Fax: + 44 (0) 1507 609154 • info@luxus.co.uk • www.luxus.co.uk

General injection moulding applications requiring good visual appearance.

Material:

Polystyrene High Impact Charcoal Black Compound

Type:

14071

Property

Specification

Units

Falling Dart Index

0.8 +

Melt Flow Index

4 - 8

g/10 mins

ISO 1133

Izod at Room Temperature

6 +

KJ/m²

ISO 180: 1993

Drying Temp

80

°C

Drying Time

2

Hrs

Packaging and COC/COA

Package options include 1000kg bulk bag or Octabox, 25Kg bag and bulk delivery. Luxus Type No grades are supplied under a certificate of conformance. A certificate of analysis can be provided upon request at an additional cost.

These are typical values for evaluation purposes and as a basis for evaluation and do not constitute any specific guarantee whatsoever.

Date

13/11/2007

Doc. No

DS14071/14