



Technical centre

Luxus Limited, Belvoir Way, Fairfield Industrial Estate, Louth, Lincolnshire, LN11 0LQ

Tel: + 44 (0) 1507 604941 • Fax: + 44 (0) 1507 609154 • info@luxus.co.uk • www.luxus.co.uk

Material:

Polypropylene Terracotta Compound

Type:

16138

Property**Specification****Units**

Melt Flow Index <i>ISO 1133</i>	30 - 45	g/10 mins
Izod at Room Temperature <i>ISO 180: 1993</i>	3 +	KJ/m ²
Load at Peak <i>ISO/R 527</i>	750	N
Stress at Peak <i>ISO/R 527</i>	18	N/mm ²

These are typical values produced for guidance and as a basis for evaluation and do not constitute any specific guarantee whatsoever.

Date

03/02/2009

Doc. No

DS16138/8