



Technical centre

Luxus Limited, Belvoir Way, Fairfield Industrial Estate, Louth, Lincolnshire, LN11 0LQ

Tel: + 44 (0) 1507 604941 • Fax: + 44 (0) 1507 609154 • info@luxus.co.uk • www.luxus.co.uk

Material:

Polypropylene Black 20% Mineral Filled Recycled Copolymer

Type:

16292

Property

Specification

Units

Melt Flow Index <i>ISO 1133</i>	18 - 22	g/10 mins
Izod at Room Temperature <i>ISO 180: 1993</i>	4.5 - 8	KJ/m ²
Load at Peak <i>ISO/R 527</i>	800 - 950	N
Stress At Peak <i>ISO/R 527</i>	20 - 24	N/mm ²
Extension <i>ISO/R 527</i>	15	%
Bend Modulus <i>ISO 178: 1993</i>	1240 - 1650	N/mm ²
Shrinkage	0.7 - 1.4	%
Drying Time	2	Hrs
Drying Temp	80	°C
Ash Test	15 M	650 °C

These are typical values produced for guidance and as a basis for evaluation and do not constitute any specific guarantee whatsoever.

Date

24/11/2008

Doc. No

DS16292/11